

Shine365 -100% Pure Acrylic Exterior Emulsion

The Product

Eureka Paints Shine365 is a 100% Pure acrylic exterior emulsion with good bacterial, UV resistance.

Key Features

Eureka Paints Shine365 is a all weather, high performance, durable coating specially designed to withstand extreme climatic conditions of high rainfall, temperature extremes and high humidity. It provides excellent bacterial and UV resistance.

Substrate Suitability

Eureka Paints Shine365 can be applied on vast range of exterior surfaces viz cement plaster, masonry, concrete, asbestos sheet ,POP, Gypsum etc.

How To Use










Surface Preparation

- Ensure that the substrate to be painted is free of any dirt, dust, oil, grease, any algae / fungal growth or any other type of contamination.
- This can be achieved by vigorous brushing of surface with media like wire, tar brush etc and cleaning with soft water.
- In case of pre painted surfaces - loose old paint etc should be thoroughly removed.
- Surfaces showing signs of chalking and flaking should be treated with some suitable sealer etc.

Touch Ups/Rectification

- Any touch up/ rectification required in the surface should be done with sand cement mortar only and it should be subjected to proper curing.
- For freshly plastered surface, care should be taken for proper curing and sufficient drying time.

Application System

Product	Application Tool	Thinner	Dilution	Touch Dry	Recoat*
Priming Eureka Paints Cement Paint	 Brush	Water	100%	1hr	2 Days After Minimum Curing - 3 Times
OR					
Eureka Paints EWP Exterior waterbase Acrylic Primer	 Brush,  Roller,  Spray	Water	60-70%	30 mins	4 hrs
1st Coat Eureka Paints Shine365 100% Pure Acrylic Exterior Emulsion	 Brush,  Roller,  Spray	Water	40-45%	1hr	4-6hrs
2nd Coat Eureka Paints Shine365 100% Pure Acrylic Exterior Emulsion	 Brush,  Roller,  Spray	Water	40-45%	1hr	4-6hrs

* Recoat period is quoted for 25°C at 50% relative humidity - may vary under different conditions.

Technical Data

1)	Covering**	On normal masonry surface brush applied 1 Coat : 10.5 - 11.5 sq mtr / ltr at recommended DFT 2 Coats : 5.5 - 6 sq mtr / ltr at recommended DFT
2)	Recommended Dry Film Thickness(DFT)	60 - 70 microns for 2 coats
3)	Weight Per Ltr	1.25 +/-0.05
4)	Gloss/Sheen Levels	0-9 on glass plate at 60°, smooth finish with slight sheen
5)	Viscosity	106KU +/- 2
6)	PH	8 to 9
7)	Thinning	40-45% by volume with water
8)	Drying Time	Touch Dry 1hr Recoat : 4-6 hrs
9)	Shelf Life	Minimum 1yr when stored in original sealed container away from sunlight and excessive heat.
10)	Pot Life	24 hrs

** Actual coverage may vary on factors such as substrate porosity, method of application etc.

Precautions

Before Use

- Do not overdilute or over extend the brush
- Stir Well Before Use

Post Application

For performance optimisation - ensure proper washing and cleaning of structures at regular intervals.

Safety

Please refer to detailed MSDS of Shine365 for detailed information on safe handling of product.



Pack Sizes & Shade Range

Pack size availability:

1ltr, 4ltr, 10ltr, 20ltr

Available in Large Shade Range

Regd. Off. : 5 Meghdoot, 2nd Floor, Plot No. 283, Flank Road, Opp. S R Mehta (Kikabhai) Hospital, Sion (E), Mumbai - 400022.

Manufactured at : Eureka Paints, Unit No. A 743, TTC Industrial Area, MIDC Village Khairne, Near Ruchit Palace Hotel, Navi Mumbai.

Customer Care :

Phone : +91-22-24096182 / 24070437 | Mobile : +91-9867466661
Email : info@eurekapaints.in | Web : www.eurekapaints.in